



Declared Performances

Application	River Training, Erosion-Control, Bank-Protection, Flood Control and Embankment-Works	
Raw material bag	Polyester	
Parameter	Value	Test-Method
Tensile strength MD	25 kN/m	EN ISO 10319
Tensile strength CMD	8.5 kN/m	EN ISO 10319
Elongation at Maximum load MD	15 %	EN ISO 10319
Elongation at Maximum load CMD	75 %	EN ISO 10319
Mass / unit	195 g/m ²	ISO 9864
Thickness @ 2 kPa	2 mm	ISO 9863-1
Static Puncture strength (CBR)	1.5 kN (-0.2 kN)	EN ISO 12236
Characteristic Opening Size O90, Maximum	No Performance determined	EN ISO 12956
Water permeability (qN), Minimum	No Performance determined	EN ISO 11058
Resistance to hydrolysis	Retained Strength: 85%	NF EN 12447
Microbiological Resistance	Retained Strength: 80%	ENV ISO 12225
Resistance to chemical degradation method A	Retained Strength: 90%	ISO TR 12960
Resistance to chemical degradation method B	Retained Strength: 90%	ISO TR 12960
Resistance to weathering	Retained Strength: 85%	EN 12224
Durability	Expected Durability of the product is minmum 25 years in Soil and in submerged conditions with temperature < 25 0C.	Product shall be covered within 1 month following installation (EN 12224 test results under certification).

The Performance of the product identified above is in conformity with the set of declared performance. This declaration of performance is issued, in accordance with regulation (EU) No 305/2011, under the sole responsibility of the manufacturer identified above.

The information in this data-sheet is provided for reference purposes only and is not intended as a warranty or guarantee Dimensions can vary based on type of fill material

Internationale Geotextil GmbH reserves the right to change the specifications from time to time



^{*} All values are average-values





Declared Performances

11	Miver Halling, Erosion Control, Bank Frotect	River Training, Erosion-Control, Bank-Protection, Flood Control and Embankment-Works	
Raw material bag	Polyester		
Parameter	Value	Test-Method	
Tensile strength MD	25 kN/m	EN ISO 10319	
Tensile strength CMD	8.5 kN/m	EN ISO 10319	
Elongation at Maximum load MD	15 %	EN ISO 10319	
Elongation at Maximum load CMD	75 %	EN ISO 10319	
Mass / unit	195 g/m²	ISO 9864	
Thickness @ 2 kPa	2 mm	ISO 9863-1	
Static Puncture strength (CBR)	1.5 kN (-0.4 kN)	EN ISO 12236	
Characteristic Opening Size O90, Maximum	No Performance determined	EN ISO 12956	
Water permeability (qN), Minimum	No Performance determined	EN ISO 11058	
Resistance to hydrolysis	Retained Strength: 85%	NF EN 12447	
Microbiological Resistance	Retained Strength: 80%	ENV ISO 12225	
Resistance to chemical degradation method A	Retained Strength: 90%	ISO TR 12960	
Resistance to chemical degradation method B	Retained Strength: 90%	ISO TR 12960	
Resistance to weathering	Retained Strength: 85%	EN 12224	
Durability	Expected Durability of the product is minmum 25 years in Soil and in submerged conditions with temperature < 25 0C.	Product shall be covered within 1 month following installation (EN 12224 test results under certification).	

The Performance of the product identified above is in conformity with the set of declared performance. This declaration of performance is issued, in accordance with regulation (EU) No 305/2011, under the sole responsibility of the manufacturer identified above.

The information in this data-sheet is provided for reference purposes only and is not intended as a warranty or guarantee Dimensions can vary based on type of fill material

Internationale Geotextil GmbH reserves the right to change the specifications from time to time



^{*} All values are average-values





Declared Performances

Application	River Training, Erosion-Control, Bank-Protection, Flood Control and Embankment-Works	
Raw material bag	Polyester	
Parameter	Value	Test-Method
Tensile strength MD	35 kN/m	EN ISO 10319
Tensile strength CMD	15 kN/m	EN ISO 10319
Elongation at Maximum load MD	15 %	EN ISO 10319
Elongation at Maximum load CMD	75 %	EN ISO 10319
Mass / unit	300 g/m ²	ISO 9864
Thickness @ 2 kPa	2.4 mm	ISO 9863-1
Static Puncture strength (CBR)	2.5 kN (-0.4 kN)	EN ISO 12236
Characteristic Opening Size O90, Maximum	No Performance determined	EN ISO 12956
Water permeability (qN), Minimum	No Performance determined	EN ISO 11058
Resistance to hydrolysis	Retained Strength: 85%	NF EN 12447
Microbiological Resistance	Retained Strength: 80%	ENV ISO 12225
Resistance to chemical degradation method A	Retained Strength: 90%	ISO TR 12960
Resistance to chemical degradation method B	Retained Strength: 90%	ISO TR 12960
Resistance to weathering	Retained Strength: 85%	EN 12224
Durability	Expected Durability of the product is minmum 25 years in Soil and in submerged conditions with temperature < 25 OC.	Product shall be covered within 1 month following installation (EN 12224 test results under certification).

The Performance of the product identified above is in conformity with the set of declared performance. This declaration of performance is issued, in accordance with regulation (EU) No 305/2011, under the sole responsibility of the manufacturer identified above.

The information in this data-sheet is provided for reference purposes only and is not intended as a warranty or guarantee Dimensions can vary based on type of fill material

Internationale Geotextil GmbH reserves the right to change the specifications from time to time



^{*} All values are average-values





Declared Performances

Application	River Training, Erosion-Control, Bank-Protection, Flood Control and Embankment-Works	
Raw material bag	Polyester	
Parameter	Value	Test-Method
Tensile strength MD	38 kN/m	EN ISO 10319
Tensile strength CMD	20 kN/m	EN ISO 10319
Elongation at Maximum load MD	15 %	EN ISO 10319
Elongation at Maximum load CMD	75 %	EN ISO 10319
Mass / unit	400 g/m ²	ISO 9864
Thickness @ 2 kPa	4 mm	ISO 9863-1
Static Puncture strength (CBR)	4.5 kN (-0.8 kN)	EN ISO 12236
Characteristic Opening Size O90, Maximum	No Performance determined	EN ISO 12956
Water permeability (qN), Minimum	No Performance determined	EN ISO 11058
Resistance to hydrolysis	Retained Strength: 85%	NF EN 12447
Microbiological Resistance	Retained Strength: 80%	ENV ISO 12225
Resistance to chemical degradation method A	Retained Strength: 90%	ISO TR 12960
Resistance to chemical degradation method B	Retained Strength: 90%	ISO TR 12960
Resistance to weathering	Retained Strength: 85%	EN 12224
Durability	Expected Durability of the product is minmum 25 years in Soil and in submerged conditions with temperature < 25 OC.	Product shall be covered within 1 month following installation (EN 12224 test results under certification).

The Performance of the product identified above is in conformity with the set of declared performance. This declaration of performance is issued, in accordance with regulation (EU) No 305/2011, under the sole responsibility of the manufacturer identified above.

The information in this data-sheet is provided for reference purposes only and is not intended as a warranty or guarantee Dimensions can vary based on type of fill material

Internationale Geotextil GmbH reserves the right to change the specifications from time to time



^{*} All values are average-values